

Model	Recommend Loading	Performance	Test Duration	Degradation Rate
eHy-1002	0.75mg/cm ²	1.96V@4A/cm ²	6000+hours @2A/cm ²	< 5μV/hr@2 A/cm ²
eHy-2001	0.50mg/cm ²	1.98V@4A/cm ²	2000+hours @2A/cm ²	< 5μV/hr@2 A/cm ²